

## Technical data

### PRODUCT – TROLDTEKT PLUS-MINERAL WOOL

Troldtekt Plus is a double-layer panel made from one 25 mm or 35 mm layer of Troldtekt acoustic panel and one 18 mm (or 40 mm) layer of mineral wool. The mineral wool panel is covered with non-woven material, and the two panels are glued together with a non-toxic PVA adhesive.

Troldtekt acoustic panels are cement-bonded wood wool panels made from wood and cement. The product consists of wood (spruce) which is shredded into wood

wool and mixed with cement. We offer PEFC™-certified or FSC®-certified Norway spruce (FSC® C115450). Both certifications guarantee that the wood comes from responsible forestry operations.

Troldtekt can be surface-treated, but is often used untreated (natural wood and natural grey). Due to the nature of the material, colour variations may occur with both natural wood and natural grey. These colour variations are most evident in the

grey panels, where the cement gives the panels the grey Troldtekt look.

Factors affecting colour variations include the water/cement ratio, the water content of the wood, the drying rate, steam curing and curing moisture.

### PRODUCT STANDARDS, LABELLING AND CERTIFICATES

#### CE marking

CE marking of building materials is required by law in the EU. The CE mark indicates that the building material in question can be legally sold and is in correspondence with the product standard to which the mark refers. Troldtekt products are CE marked, and in addition to the marking, we state:

Name of the producer:  
Troldtekt A/S

Certificate numbers:  
0615 – CPD – 222958G  
0615 – CPD – 804474G

Product standard number:  
EN 13168 and EN 13964

Declaration:  
See product data on page 2.

#### Other approvals

Indoor climate certification: Troldtekt is certified to the best indoor climate categories by the Danish Indoor Climate Labelling (*Dansk Indeklima Mærkning*)

Ball impact certification: A wide range of structures with Troldtekt acoustic panels have been tested and certified for use as ceiling and wall cladding in sports facilities in accordance with 'Prüfung der Ballwurfsicherheit, DIN 18032 Teil 3, Sportshallen für Turnen und Spiele' (requirements and testing of ball impact safety, DIN 18032, Part 3, sports facilities). EN 13964 also includes ball impact certification as a parameter, and here Troldtekt is classified as Class 1A.

#### International approvals:

SP Sitac – Sweden  
Nemko – Norway  
Komo – Netherlands  
MK – Denmark

#### Light reflection

Light reflection for different types of Troldtekt panels (measured by DELTA Light and Optics):

Troldtekt white 101	70.8%
Troldtekt natural wood	55.2%
Troldtekt natural grey	26.3%

### USE AND MAINTENANCE

Troldtekt panels usually require no subsequent care. However, we recommend regular cleaning along with other surfaces – and otherwise as required. Light cleaning of the panels is easy using a vacuum cleaner with a brush nozzle. If vacuum-cleaning is not sufficient, you can wipe the panels

using a well wrung cloth. If you subsequently want to paint the Troldtekt ceiling, you can use a long-haired paint roller or a hand sprayer. Water-based paint will not negatively impact the sound-absorbent properties of the panels.

## RECYCLING

All Troldtekt cement-bonded wood wool products can be composted and safely returned to nature as a soil conditioner. The cement in Troldtekt's acoustic panels boosts oxygen levels during the composting process, while the wood adds organic material to the compost.

## TOLERANCES

It is important to note that Troldtekt is a natural material and the very nature of the material composition – wood wool and cement – will incur small variations in the panels. Panel dimensions and weights remain inside the tolerance indicated at

23 +/- 2°C and 50 +/- 5% relative humidity. However, inappropriate storage and lack of acclimatisation could alter panel dimension and weight. It is therefore important that you observe the installation, storage and acclimatisation instructions carefully.

## PRODUCT DATA

The table below indicates the tolerances declared by us in accordance with EN 13168, the standard for cement-bonded wood wool and double-layer panels with cement-bonded wood wool, and EN 13964, the standard for suspended ceilings.

### Properties:

#### DIMENSIONS

Width (mm)	600			
Length (mm)	600/2400			
Thickness (mm)	43	53	65	75
	(25+18)	(35+18)	(25+40)	(35+40)

#### Weight (kg/m<sup>2</sup>)

Fine	11,0	13,3	12,5	14,8
Ultrafine	11,9	14,6	13,4	16,1
Extreme fine	13,0	15,5	14,5	17,0

#### TOLERANCES

Length (mm)	≥ 1.250 : ±2.0
	≤ 1.250 : ±1.0
Width (mm)	±1.0
Thickness (mm)	Length ≥ 1.250 : ±2.0
	Length ≤ 1.250 : ±1.0
% by weight	±10
Perpendicularity (mm/m)	±≤2
Planeness (mm)	±≤3

#### HEAT

Lambda value W/m·K	0.052 (43 mm)
	0.055 (53 mm)
	0.045 (65 mm)
	0.048 (75 mm)

#### FIRE

Reaction to fire	B/s1/d0
------------------	---------

#### IMPACT RESISTANCE

Ball impact certification	1A
---------------------------	----

#### SUBSTANCES

Chloride %	≤0.06
Formaldehyde	E1*

#### INDOOR CLIMATE

Degassing	10 days
Particle release	Low

#### STANDARD

Declared in accordance with	EN 13168
	EN 13964

\* No measurable formaldehyde emission

Troldtekt A/S  
Sletvej 2A  
DK - 8310 Tranbjerg J  
Tel. +45 8747 8100  
Fax +45 8747 8111  
info@troldtekt.dk  
www.troldtekt.com